



NICKEL BARS ROLLED DEPOLARIZED

PRODUCT SPECIFICATIONS

	TYPICAL ASSAY
Nickel	99.00 %
Iron	0.15% max
Manganese	0.05% max
Copper	0.10% max
Silicon	0.02% max
Sulfur	0.01% max
Carbon	0.20% max
Oxygen	0.20% max